

PRODUCT INFORMATION DATA SHEET

LIBNOL G-200

DESCRIPTION : Oleochemical Derivative

SPECIFICATIONS :

Appearance	Flakes
Acid Value	200 Min.
Iodine Value	3 Max.
Melting Point	54 - 56°C

PROPERTIES :

- External Lubricant
- Improved non-stickiness

APPLICATIONS :

For PVC :

External Lubricant for Rigid and Soft PVC

For Other Plastics :

Ideal lubricant for PMMA

Release Agent for Synthetic Rubbers.

DOSAGE :

0.2 - 0.5 phr for Rigid PVC

0.2 - 0.5 phr for Soft PVC

0.1 - 0.5 phr for PMMA

1.0 - 2.0 phr for Synthetic Rubbers