

PRODUCT INFORMATION DATA SHEET

LIBWAX PE-I

DESCRIPTION	:	Oxidised Polyethylene wax
SPECIFICATIONS	:	Appearance : White Beads
		Acid Value : 15 Max.
		Melting Point : 99 - 102°C
		Melt Viscosity : 250 - 300 cps at 140°C
APPLICATIONS	:	LIBWAX PE-I is an external lubricant for CPVC calendaring, Extrusion and Injection Molding. LIBWAX PE-I does not affect transparency of the product when used @ 0.1 to 0.15 phr.
DOSAGE	:	0.8 - 1.0 phr
STABILIZATION	:	Suitable for use with all Commercially available Stabilizers (Pb, Tin, Ba-Cd).