

PRODUCT INFORMATION DATA SHEET

**LIBWAX PE-2**

- DESCRIPTION** : Partially Oxidised Polyethylene wax
- SPECIFICATIONS** : Appearance : Powder  
Melting Point : 107 - 108°C  
Melt Viscosity : 200 - 250 cps at 140°C
- PROPERTIES** : Injection molding demands high flow with improved stability, Libwax PE-2 acts as lubricant during processing and improves flow without affecting HDT.
- APPLICATIONS** : ☉ PVC, OPVC and CPVC pipe and fittings.  
☉ One Pack Stabilizer manufacturing.
- DOSAGE** : 2 Phr for CPVC fitting compound.