

## PRODUCT INFORMATION DATA SHEET

# LIBNOL G-121

<b>DESCRIPTION</b>	:	Oleochemical Derivative
<b>SPECIFICATIONS</b>	:	Appearance : Creamish Powder Acid Value : 3 Max. Iodine Value : 5 Max. Melting Point : 58 - 60°C
<b>PROPERTIES</b>	:	<ul style="list-style-type: none"><li>• Internal Lubricant</li><li>• Good Compatibility</li><li>• Improved free-flowing properties</li><li>• Suitable for use in transparent products at amounts of less than 1%.</li></ul>
<b>APPLICATIONS</b>	:	<p><b><u>For PVC :</u></b> Processing Rigid PVC - extrusion and Molding.</p> <p><b><u>For Other Plastics :</u></b> Ideal Lubricant for PU</p>
<b>DOSAGE</b>	:	0.5 - 1.5% for Rigid PVC 0.5 - 1.0% for PU
<b>NON-APPLICATION</b>	:	With lead stabilizers in rigid PVC, brightly pigmented if climatic influences are to be expected.