

## PRODUCT INFORMATION DATA SHEET

# LIBNOL G-2I

<b>DESCRIPTION</b>	:	Oleochemical Derivative
<b>SPECIFICATIONS</b>	:	Appearance : Creamish Powder / Flakes Acid Value : 3 Max. Iodine Value : 3 Max. Melting Point : 58 - 60°C
<b>APPLICATIONS</b>	:	<ul style="list-style-type: none"><li>• Processing rigid and Semi rigid PVC</li><li>• By Extrusion, Injection moulding.</li></ul> <p><b><i>Specially suggested for use in Manufacturing of</i></b></p> <ul style="list-style-type: none"><li>• Rigid PVC Pipes/Profiles/Conduits, Rigid PVC Fittings/Moulded Parts, PVC Cable/Footwear Compounds</li></ul>
<b>PROPERTIES</b>	:	<ul style="list-style-type: none"><li>• Intermediate Lubricant</li><li>• Good Compatibility</li></ul>
<b>DOSAGE</b>	:	0.5 - 1.5 phr for Rigid PVC 0.5 - 1.5 phr for Soft PVC
<b>STABILISATION</b>	:	Suitable for use with all commercially-available stabilizers. (Pb,Tin, Ba-cd, Ba-zn etc.)