

## PRODUCT INFORMATION DATA SHEET

# LIBWAX PE-I

<b>DESCRIPTION</b>	:	Oxidised Polyethylene wax
<b>SPECIFICATIONS</b>	:	Appearance : White Beads
		Acid Value : 15 Max.
		Melting Point : 99 - 102°C
		Melt Viscosity : 250 - 300 cps at 140°C
<b>APPLICATIONS</b>	:	LIBWAX PE-I is an external lubricant for PVC calendaring, Extrusion and Injection Molding. LIBWAX PE-I does not affect transparency of the product when used @ 0.1 to 0.15 phr.
<b>DOSAGE</b>	:	0.1 - 0.15 phr
<b>STABILIZATION</b>	:	Suitable for use with all Commercially available Stabilizers (Pb, Tin, Ba-Cd).